
Composure

Interface®

4169-006-000 Seclusion



Installation Methods



All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclamer

and Crocking

Colour Fastness to Rubbing

Colour Fastness to Water

Flammability - Methenamine

Flammability - Radiant Panel

Flammability - Smoke

Density

Antistatic

| | Interrace |
|--------------------------------------|--|
| Product Composure | Colour Seclusion Collection Composure |
| Product Number | 4169 |
| Product Specificat | tions |
| Product Construction | Tufted Textured Loop |
| Yarn System | 100% Solution Dyed Nylon |
| Dye Method | 100% Solution Dyed |
| Soil/Stain Protection | Protekt ^{2®} |
| Preservative Protection | Intersept [®] |
| More Product Spe | cifications |
| Machine Gauge | 12th Gauge |
| Stitches | 34.5/10cm 8.8/in |
| Pile Thickness | 2.0mm ±0.5mm |
| Total Thickness | 6.0mm ±0.5mm |
| Backing Structure | GlasBac™ |
| Performance Spec | cifications |
| Area of Use | Commercial Heavy Use |
| Stability - Delaminating | ASTM D3936 ≥ 3.0 lbs/in GB/T 26843 ≥ 26 N |
| Stability - Dimensional Stability | ISO $2551 \le \pm 0.1\%$ QB/T $2755 \le 0.1\%$ |
| Stability - Tuft Bind | QB/T 1090 ≥ 24 N (QB/T 2755) ISO 4919 > 30 N |
| Wear - Castor Chair | QB/T $2755 \le 0.15\%$ EN 985 > 2.4 Rating @25,000 cycles |
| Wear - Vetterman Drum | GB/T 26844 \geq 3.0 at 22000 cycles ISO 10361(ASTM D5417) \geq 3.5 Rating @20,000 cycles |
| Colour Fastness to Ligh | GB/T 8427 ≥ 4-5 |

AATCC 16 Part 3 ≥ 4 @ 60 Hours

AATCC 165 \geq 4 (Wet & Dry)

GB/T 3920 ≥ 4-5

AATCC 107 ≥ 4

GB/T 5713 ≥ 4-5

ASTM E662 < 450

AATCC 134 < 3.0 kV

GB/T $18044 \le 2.0 \text{ kV}$

GB/T 11049 \leq 25.4 mm

ASTM 2859 - 7 of 8 passing

ASTM E648 > .45 watts/sq. cm

GB/T 11785 B1 CHF≥ 4.5 kW/m² (GB 8624)

GB/T 11785 s1 \leq 750 %.min (GB 8624)

| Lifetime Antimicrobial | AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition |
|---------------------------------------|--|
| Generic Tests | |
| Acoustic - Nylon | Absorption Coefficient - NRC 0.0 - 0.2 |
| Dynamic Loading | ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss |
| Static Loading | ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss |
| Green Carpet (VOC) | ASTM D5116 Accredited ISO 10580 Accredited |
| Thermal Resistance | ASTM C518 R Value ≥ 0.5 |
| Environmental Specific | ations |
| Recycled Content % | 58% |
| Pre-Consumer (Total) | 56% |
| Post-Consumer (Total) | 2% |
| Other Environmental Claims | View Environmental Accreditations |
| Ingredients and Life Cycle Impacts | Environmental Product Declaration - GlasBac™ |
| End of Life | Carpet to Carpet Recycling |
| Embodied Carbon (Cradle to Gate) | 5.41 kg CO ₂ eq./m ² |
| Technical Information | |
| Installation | View recommended Interface Installation Guidelines online |
| Maintenance | View recommended Interface Maintenance Guidelines online |
| Reclamation | View details on our ReEntry™ Program |
| Warranty | 15 Year Standard Warranty |
| Manufacturing Location | ISO9001&14001&45001 Certified Plant in Taicang ☐ China |