

Shishu Stitch [-CO2]

Interface®


9553-002-000 Shade



安装方式



上下错拼



人字形

所有产品的规格信息由测试样品的平均值推算而出，受产品的生产工艺及内在的差异影响，会存在合理的偏差范围，最终解释权归英特飞模块地毯(中国)有限公司。更多关于产品信息的声明请查看www.interface.com.cn/page/disclamer

样式名 Shishu Stitch [-CO2] 颜色名 Shade 系列名 Embodied Beauty

产品编号 9553

产品规格

产品结构 Tufted Textured Loop

纱线系统 100% Solution Dyed Nylon

染色方式 100% Solution Dyed

更多产品规格

簇绒机规格 12th Gauge

针密 67/10cm-17.02/in

毯毛厚度 2.0mm ±0.5mm

地毯总厚度 5.7mm ±0.5mm

产品尺寸 25*100

标准底背 CQuest™BioX

性能指标

应用区域 Commercial - Heavy Use

稳定性-剥离强度 AS/NZS 2111.16 ≥ 50 Newtons
ASTM D3936 ≥ 2.5lbs/in

稳定性-尺寸稳定性 ISO 2551 ≤ 0.2%
ISO/PAS 17984 < 0.2%

稳定性-簇绒拔出力 ASTM D1335 ≥ 8.0 lbs
AS/NZS 2111.15 >30 Newtons

磨损性 - 脚轮椅 BS-EN 985 r ≥ 2.4

磨损性 - 威特曼鼓轮或六足滚筒 TWC-TM247 / TWC-TM251 / TWC-TM284 Colour: ≥3 & Structure: ≥3,BS ISO 10361 Overall Change ≥3.5 (Heavy Contract)

耐光色牢度 AS2001 1.4.21 ≥ 4
AATCC 16E ≥ 4

耐摩擦色牢度 AATCC 165 ≥ 4
AS/NZS2111.19.1 ≥ 4

耐水色牢度 AATCC 107 ≥ 4
AS2001.4.21 ≥ 4

阻燃性 - 乌洛托品(甲胺)测试 BS6307/ISO 6925 Radius ≤ 7.6

阻燃性 - 热源辐射测试 ASTM E648 Class 1
ISO 9239-1 B1

阻燃性 - 烟气密度 ASTM E662 Density ≤ 450
ISO 9239-1 Density < 750 %.min

抗静电性 AATCC 134 < 3000 Volts
BS ISO 6356 ≤ 2.0Kv

抗菌处理	ASTM E2471 Complete Inhibition AATCC 171 Washed AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days
------	--

通用测试

吸音性	Absorption Coefficient - NRC $\geq$ 0.10
动态负载	AS/NZS 2111.2 < 12.5% loss ISO 2094 $\geq$ 85%
静态负载	AS/NZS2111.13 < 6% Loss
VOC	ASTM D5116 Accredited ISO 10580 Accredited
热阻	ASTM C518 R Value $\geq$ 0.5

环境指标

回收成分含量 %	34%
消费前回收	33%
消费后回收	1%
室内空气质量	Green Label Plus #GLP100209
产品可持续性	NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard
成分与生命周期影响	Environmental Product Declaration - CQuest™BioX
产品寿命末期	Carpet to Carpet Recycling
隐含碳排放(从摇篮到大门)	-0.3 kg CO ₂ eq./m ²

技术资料

安装指南	View recommended Interface Installation Guidelines online
维护指南	View recommended Interface Maintenance Guidelines online
回收再利用	View details on our ReEntry™ Program
质保	15 Year Standard Warranty
制造工厂	ISO 9001 & 14001 & 45001 Certified Facilities in Europe