



4169-006-000 Seclusion



Installation Methods



Non Directional

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclaimer

Product Composure Colour Seclusion Collection Composure

Product Number 4169

Product Specifications

Product Construction Tufted Textured Loop

Yarn System 100% Solution Dyed Nylon

Dye Method 100% Solution Dyed

Soil/Stain Protection [Protekt2®](#)

Preservative Protection Intersept®

More Product Specifications

Machine Gauge 12th Gauge

Stitches 34.5/10cm 8.8/in

Pile Thickness 2.0mm ±0.5mm

Total Thickness 6.0mm ±0.5mm

Backing Structure GlasBac™

Performance Specifications

Area of Use Commercial Heavy Use

Stability - Delaminating ASTM D3936 ≥ 3.0 lbs/in
GB/T 26843 ≥ 26 N

Stability - Dimensional Stability ISO 2551 ≤ ± 0.1%
QB/T 2755 ≤ 0.1%

Stability - Tuft Bind QB/T 1090 ≥ 24 N (QB/T 2755)
ISO 4919 > 30 N

Wear - Castor Chair QB/T 2755 ≤ 0.15%
EN 985 > 2.4 Rating @25,000 cycles

Wear - Vetterman Drum GB/T 26844 ≥ 3.0 at 22000 cycles
ISO 10361(ASTM D5417) ≥ 3.5 Rating @20,000 cycles

Colour Fastness to Light GB/T 8427 ≥ 4-5
AATCC 16 Part 3 ≥ 4 @ 60 Hours

Colour Fastness to Rubbing and Crocking GB/T 3920 ≥ 4-5
AATCC 165 ≥ 4 (Wet & Dry)

Colour Fastness to Water AATCC 107 ≥ 4
GB/T 5713 ≥ 4-5

Flammability - Methanamide Pill GB/T 11049 ≤ 25.4 mm
ASTM 2859 - 7 of 8 passing

Flammability - Radiant Panel GB/T 11785 B1 CHF ≥ 4.5 kW/m² (GB 8624)
ASTM E648 > .45 watts/sq. cm

Flammability - Smoke Density ASTM E662 < 450
GB/T 11785 s1 ≤ 750 %.min (GB 8624)

Antistatic AATCC 134 < 3.0 kV
GB/T 18044 ≤ 2.0 kV

Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition
------------------------	---

Generic Tests

Acoustic – Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss
Static Loading	ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Thermal Resistance	ASTM C518 R Value 0.5

Environmental Specifications

Recycled Content %	58%
Pre-Consumer (Total)	56%
Post-Consumer (Total)	2%
Other Environmental Claims	View Environmental Accreditations
Ingredients and Life Cycle Impacts	Environmental Product Declaration - GlasBac™
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.41 kg CO ₂ eq./m ²

Technical Information

Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance Guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty
Manufacturing Location	ISO9001&14001&45001 Certified Plant in Taicang, China