Interface®

2415-001-000 Harmony



Installation Methods





All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclamer

| Product FT520 | Colour Harmony | Collection Fading Tracks |
|---------------|----------------|---------------------------------|
| | | |

Product Number 2415

Product Specifications

| Product Construction | Tufted Textured Loop |
|-------------------------|--------------------------|
| Yarn System | 100% Solution Dyed Nylon |
| Dye Method | 100% Solution Dyed |
| Soil/Stain Protection | Protekt ^{2®} |
| Preservative Protection | Intersept® |

More Product Specifications

| Machine Gauge | 12th Gauge |
|-------------------|----------------------|
| Stitches | 44/10cm - 11.2/in |
| Pile Thickness | 2.5mm ±0.5mm |
| Total Thickness | 5.5mm ±0.5mm |
| Size Description | 25*100 |
| Backing Structure | GlasBac [®] |

Performance Specifications

| Area of Use | Commercial - Heavy Use |
|---|--|
| Stability - Delaminating | AS/NZS 2111.16 ≥ 50 Newtons ASTM D3936 ≥ 2.5lbs/in |
| Stability - Dimensional Stability | ISO 2551 ≤ 0.2% ISO/PAS 17984 < 0.2% |
| Stability - Tuft Bind | ASTM D1335 ≥ 8.0 lbs AS/NZS 2111.15 >30 Newtons |
| Wear - Castor Chair | BS-EN 985 r ≥ 2.4 |
| Wear - Vetterman Drum | BS ISO 10361 Overall Change ≥3.0 (Heavy Contract),TWC-TM247 / TWC-TM251 / TWC-TM284 Colour: ≥3 & Structure: ≥3 |
| Colour Fastness to Light | AS2001 1.4.21 ≥ 4 AATCC 16E ≥ 4 |
| Colour Fastness to Rubbing and Crocking | AATCC 165 ≥ 4 AS/NZS2111.19.1 ≥ 4 |
| Colour Fastness to Water | AATCC 107 ≥ 4 AS2001.4.21 ≥ 4 |
| Flammability - Methanamile Pill | BS6307/ISO 6925 Radius ≤ 7.6 |
| Flammability - Radiant Panel | ASTM E648 Class 1 ISO 9239-1 B1 |
| Flammability - Smoke Density | ASTM E662 Density ≤ 450 ISO 9239-1 Density < 750 %.min |
| | |

| Antistatic | AATCC 134 < 3000 Volts BS ISO 6356 ≤ 2.0Kv | |
|---------------------------------------|---|--|
| Lifetime Antimicrobial | AATCC 171 Washed ASTME-2471 Complete Inhibition AATCC174 Parts 2 & 3 99% reduction. No mold 7 Days | |
| Generic Tests | | |
| Acoustic - Nylon | Absorption Coefficient - NRC ≥ 0.10 | |
| Dynamic Loading | AS/NZS 2111.2 < 12.5% loss ISO 2094 ≥ 85% | |
| Static Loading | AS/NZS2111.13 < 6% Loss ISO 015/3415 Thickness after 60 mins recovery >85% | |
| Green Carpet (VOC) | ASTM D5116 Accredited ISO 10580 Accredited | |
| Thermal Resistance | ASTM C518 R Value ≥ 0.5 | |
| Environmental Specific | ations | |
| Recycled Content % | 59% | |
| Pre-Consumer (Total) | 57% | |
| Post-Consumer (Total) | 2% | |
| Indoor Air Quality | Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420 | |
| NSF Sustainable Carpet | NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard | |
| Ingredients and Life Cycle Impacts | Environmental Product Declaration - GlasBac® | |
| End of Life | Carpet to Carpet Recycling | |
| Embodied Carbon (Cradle to Gate) | 4.9 kg CO ₂ eq./m ² | |
| Technical Information | | |
| Installation | View recommended Interface Installation Guidelines online | |
| Maintenance | View recommended Interface Maintenance Guidelines online | |
| Reclamation | View details on our ReEntry™ Program | |
| Warranty | 15 Year Standard Warranty | |
| Manufacturing Location | ISO9001&14001&45001 Certified Plant in Taicang\(\text{China} \) | |