



Composure Edge

Interface®

2490-006-000
Sapphire/diffuse



Installation Methods



Non Directional

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see www.interface.com.cn/page/disclamer

Product Composure Edge	Colour Sapphire/diffuse	Collection Composure
Product Number	2490	
Product Specifications		
Product Construction	Tufted Textured Loop	
Yarn System	100% Solution Dyed Nylon	
Dye Method	100% Solution Dyed	
Soil/Stain Protection	Protekt ² ®	
Preservative Protection	Intersept [®]	
More Product Specifications		
Machine Gauge	12th Gauge	
Stitches	39/10cm 10/in	
Pile Thickness	3.0mm ±0.5mm	
Total Thickness	6.0mm ±0.5mm	
Size Description	50*50	
Backing Structure	GlasBac [®]	
Performance Specifications		
Area of Use	Commercial - Heavy Duty	
Stability - Delaminating	ASTM D3936 ≥ 3.0 lbs/in ISO 11857 ≥ 26 N GB/T 26843 ≥ 26 N	
Stability - Dimensional Stability	ISO 2551 ≤ 0.1% QB/T 2755 ≤ 0.1%	
Stability - Tuft Bind	ASTM D1335 ≥ 8.0 lbs ISO 4919 ≥ 30 N QB/T 1090 ≥ 24 N (QB/T 2755)	
Wear - Castor Chair	ISO 4918 ≥ 2.4 QB/T 2755 ≤ 0.15%	
Wear - Vetterman Drum	ASTM D5252 ≥ 3.0 at 12000 cycles ISO 10361 ≥ 3.0 at 22000 cycles GB/T 26844 ≥ 3.0 at 22000 cycles	
Colour Fastness to Light	AATCC 16E ≥ 4 at 60 AFU's ISO 105-B02 ≥ 4-5 GB/T 8427 ≥ 4-5	
Colour Fastness to Rubbing and Crocking	AATCC 165 ≥ 4 ISO 105-X12 ≥ 4-5 GB/T 3920 ≥ 4-5	
Colour Fastness to Water	AATCC 107 ≥ 4 ISO 105-E01 ≥ 4-5 GB/T 5713 ≥ 4-5	

Flammability - Methanamide Pill	Pass DOC FF 1-70 or ASTM D2859 Test ISO 6925 $\leq$ 25.4 mm GB/T 11049 $\leq$ 25.4 mm
Flammability - Radiant Panel	ASTM E648 Class 1 ISO 9239-1 B1 CHF $\geq$ 4.5 kW/m ² (GB 8624) GB/T 11785 B1 CHF $\geq$ 4.5 kW/m ² (GB 8624)
Flammability - Smoke Density	ASTM E662 $<$ 450 ISO 9239-1 $\leq$ 750 %.min (GB 8624) GB/T 11785 s1 $\leq$ 750 %.min (GB 8624)
Antistatic	AATCC 134 $<$ 3.0 kV ISO 6356 $\leq$ 2.0 kV GB/T 18044 $\leq$ 2.0 kV
Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition

Generic Tests

Acoustic - Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 $<$ 15% Thickness loss QB/T 1091 $<$ 15% Thickness loss
Static Loading	ISO 3415 $<$ 15% Thickness loss QB/T 1092 $<$ 15% Thickness loss
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Thermal Resistance	ASTM C518 R Value 0.5

Environmental Specifications

Recycled Content %	58%
Pre-Consumer (Total)	56%
Post-Consumer (Total)	2%
Indoor Air Quality	Green Label Plus ASTM D5116 # GLP1354 UL GREENGUARD Gold UL 2818 # 71238-420
NSF Sustainable Carpet	NSF/ANSI 140 Gold Sustainable Carpet Assessment Standard
Ingredients and Life Cycle Impacts	Environmental Product Declaration - GlasBac®
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.92 kg CO ₂ eq./m ²

Technical Information

Installation	View recommended Interface Installation Guidelines online
Maintenance	View recommended Interface Maintenance Guidelines online
Reclamation	View details on our ReEntry™ Program
Warranty	15 Year Standard Warranty
Manufacturing Location	ISO9001&14001&45001 Certified Plant in Taicang, China