



# 2544-002-000 Storm



## Installation Methods



Ashlar



Herringbone

All product specifications reflect averages derived from product sample testing, are subject to normal manufacturing and testing tolerances and inherent pattern variances, and may be changed without notice. For more information about these and other important attributes of the product(s) described herein, including recycled content and product warranty information, please see [www.interface.com.cn/page/disclaimer](http://www.interface.com.cn/page/disclaimer)

**Product** Works+Fluid **Colour** Storm **Collection** Works+ Series

Product Number 2544

## Product Specifications

Product Construction	Tufted Textured Loop
Yarn System	100% Solution Dyed Nylon
Dye Method	100% Solution Dyed
Soil/Stain Protection	Protekt®
Preservative Protection	Intersept®

## More Product Specifications

Machine Gauge	12th Gauge
Stitches	40/10cm 10.16/in
Pile Thickness	2.5mm ±0.5mm
Total Thickness	6.5mm ±0.5mm
Backing Structure	GlasBac™

## Performance Specifications

Area of Use	Commercial General Use
Stability - Delaminating	ASTM D3936 ≥ 3.0 lbs/in GB/T 26843 ≥ 26 N
Stability - Dimensional Stability	ISO 2551 ≤ ± 0.1% QB/T 2755 ≤ 0.1%
Stability - Tuft Bind	QB/T 1090 ≥ 24 N (QB/T 2755) ISO 4919 > 30 N
Wear - Castor Chair	QB/T 2755 ≤ 0.15% EN 985 > 2.4 Rating @25,000 cycles
Wear - Vetterman Drum	GB/T 26844 ≥ 3.0 at 22000 cycles TWC-TM247/251/284 Colour: ≥3 & Structure: ≥3
Colour Fastness to Light	GB/T 8427 ≥ 4-5 AATCC 16 Part 3 ≥ 4 @ 60 Hours
Colour Fastness to Rubbing and Crocking	GB/T 3920 ≥ 4-5 AATCC 165 ≥ 4 (Wet & Dry)
Colour Fastness to Water	AATCC 107 ≥ 4 GB/T 5713 ≥ 4-5
Flammability - Methenamine Pill	GB/T 11049 ≤ 25.4 mm ASTM 2859 - 7 of 8 passing
Flammability - Radiant Panel	GB/T 11785 B1 CHF≥ 4.5 kW/m² (GB 8624) ASTM E648 > .45 watts/sq. cm
Flammability - Smoke Density	ASTM E662 < 450 GB/T 11785 s1 ≤ 750 %.min (GB 8624)
Antistatic	AATCC 134 < 3.0 kV GB/T 18044 ≤ 2.0 kV

Lifetime Antimicrobial	AATCC 174 Parts II & III 99% reduction/No mold 7 Days ASTM E2471 Complete Inhibition
------------------------	---

### Generic Tests

Acoustic – Nylon	Absorption Coefficient - NRC 0.0 - 0.2
Dynamic Loading	ISO 2094 < 15% Thickness loss QB/T 1091 < 15% Thickness loss
Static Loading	ISO 3415 < 15% Thickness loss QB/T 1092 < 15% Thickness loss
Green Carpet (VOC)	ASTM D5116 Accredited ISO 10580 Accredited
Thermal Resistance	ASTM C518 R Value $\geq$ 0.5

### Environmental Specifications

Recycled Content %	46%
Pre-Consumer (Total)	45%
Post-Consumer (Total)	1%
Other Environmental Claims	<a href="#">View Environmental Accreditations</a>
Ingredients and Life Cycle Impacts	<a href="#">Environmental Product Declaration - GlasBac™</a>
End of Life	Carpet to Carpet Recycling
Embodied Carbon (Cradle to Gate)	5.67 kg CO <sub>2</sub> eq./m <sup>2</sup>

### Technical Information

Installation	<a href="#">View recommended Interface Installation Guidelines online</a>
Maintenance	<a href="#">View recommended Interface Maintenance Guidelines online</a>
Reclamation	<a href="#">View details on our ReEntry™ Program</a>
Warranty	<a href="#">15 Year Standard Warranty</a>
Manufacturing Location	<a href="#">ISO9001&amp;14001&amp;45001 Certified Plant in Taicang, China</a>